

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Gold Reference Material Product Code

G301-1


Certified Control Values

50 gram Fire Assay

Gold Grade	0.85 ppm
Standard Deviation	0.05 ppm
Confidence Interval	+/- 0.01 ppm

Aqua Regia Digest

Gold Grade	0.83 ppm
Standard Deviation	0.10 ppm
Confidence Interval	+/- 0.026 ppm



CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm)		Major Elements Fusion / XRF (%)	
	<p>Control statistics were produced from results accumulated in the :</p> <p><u>April-2001</u> Geostats Pty Ltd Laboratory Round Robin Program.</p> <p><u>91</u> laboratories tested this material using 50 gram Fire Assay.</p> <p><u>55</u> laboratories tested it using an Aqua Regia Technique.</p> <p>Source Material Prior to homogenisation and testing, this material was sourced from Gold Ore ex Eastern Goldfields</p> <p>Colour Designation Light gray</p> <p>Usage This product is for use in the mining industry as reference materials for monitoring and testing the accuracy of laboratory assaying.</p> <p>Preparation and Packaging All standards are dried in an oven for a minimum of 12 hours at 110C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an Air Classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.</p> <p>Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.</p> <p>Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by a minimum of 50 reputable laboratories selected from across the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.</p>	<p>Antimony <0.2</p> <p>Arsenic <1</p> <p>Barium <100</p> <p>Bromine <1</p> <p>Cadmium nr</p> <p>Cerium 34.5</p> <p>Caesium <1</p> <p>Chromium 181</p> <p>Cobalt 36.2</p> <p>Europium 1.84</p> <p>Gold ppb 840</p> <p>Hafnium 3.16</p> <p>Iridium ppb <20</p> <p>Iron % 8.53</p> <p>Lanthanum 11.9</p> <p>Lutetium 0.38</p> <p>Molybdenum <5</p> <p>Nickel nr</p> <p>Rubidium 35.6</p> <p>Samarium 5.34</p> <p>Scandium 33.2</p> <p>Selenium <5</p> <p>Sodium % 2.34</p> <p>Tantalum <1</p> <p>Tellurium <5</p> <p>Terbium nr</p> <p>Thorium 1.37</p> <p>Tin nr</p> <p>Tungsten <2</p> <p>Uranium <2</p> <p>Ytterbium 2.99</p> <p>Zinc 175</p> <p>Zirconium <500</p> <p>Calcium% 5.94</p> <p>Potassium % 0.74</p> <p>Silver <5</p> <p>Mercury nr</p> <p>Neodymium nr</p> <p>Strontium nr</p>	<p>Fe nr</p> <p>SiO2 nr</p> <p>Al2O3 nr</p> <p>TiO2 nr</p> <p>MnO nr</p> <p>CaO nr</p> <p>P nr</p> <p>S nr</p> <p>MgO nr</p> <p>K2O nr</p> <p>Na2O nr</p> <p>LOI1000 nr</p>	

10A Marsh Close, O'Connor, Western Australia 6163
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699
e-mail : pjh@geostats.com.au, srr@geostats.com.au
Website <http://www.geostats.com.au>

G301-1

Geostats Pty Ltd, Certified Gold Reference Material, Product Code :