

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales


Certified Gold Reference Material Product Code

G301-13

Certified Control Values

50 gram Fire Assay	
Gold Grade	1.68 ppm
Standard Deviation	0.08 ppm
Confidence Interval	+/- 0.009 ppm

Aqua Regia Digest	
Gold Grade	1.65 ppm
Standard Deviation	0.13 ppm
Confidence Interval	+/- 0.017 ppm



CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm)		Major Elements Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the : <u>October-2004</u> Geostats Pty Ltd Laboratory Round Robin Program. <u>332</u> laboratories tested this material using 50 gram Fire Assay. <u>232</u> laboratories tested it using an Aqua Regia Technique.	Antimony	<0.2	Fe
Source Material Prior to homogenisation and testing, this material was sourced from Low Sulphide Ore Ex Eastern Goldfields	Arsenic	<1	SiO2	nr
Colour Designation Light gray	Barium	<100	Al2O3	nr
Usage This product is for use in the mining industry as reference materials for monitoring and testing the accuracy of laboratory assaying.	Bromine	<1	TiO2	nr
Preparation and Packaging All standards are dried in an oven for a minimum of 12 hours at 110C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an Air Classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	<5	MnO	nr
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by a minimum of 50 reputable laboratories selected from across the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cerium	25.83333	CaO	nr
	Caesium	<1	P	nr
	Chromium	188.3333	S	nr
	Cobalt	41.33333	MgO	nr
	Europium	2.103333	K2O	nr
	Gold ppb	1796.667	Na2O	nr
	Hafnium	4.213333	LOI1000	nr
	Iridium ppb	<20		
	Iron %	8.866667		
	Lanthanum	10.4		
	Lutetium	0.453333		
	Molybdenum	<5		
	Nickel	40.5		
	Rubidium	16.55		
	Samarium	5.35		
	Scandium	34.3		
	Selenium	<5		
	Sodium %	2.193333		
	Tantalum	<1		
	Tellurium	<5		
	Terbium	1.35		
	Thorium	1.38		
	Tin	<100		
	Tungsten	<2		
	Uranium	<2		
	Ytterbium	3.106667		
	Zinc	202		
	Zirconium	<500		
	Calcium%	7.065		
	Potassium %	0.37		
	Silver	<5		
	Mercury	nr		
	Neodymium	nr		
	Strontium	nr		

10A Marsh Close, O'Connor, Western Australia 6163
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699
e-mail : pjh@geostats.com.au, srr@geostats.com.au
Website <http://www.geostats.com.au>

G301-13

Geostats Pty Ltd, Certified Gold Reference Material, Product Code :