

**Mining Industry Consultants
Reference Material Manufacture and Sales**

G397-6

Gold Grade	3.82 ppm
Standard Deviation	0.27 ppm
Confidence Interval	+/- 0.071 ppm

Control Statistic Details Control statistics were produced from results accumulated in the April-1997 round robin. A total of 57 fire assay results and 59 results from an aqua regia technique were used to certify this material.		Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)			
Material Description This material is described as a Laterite ore.		Antimony	2.68	Fe	nr		
		Arsenic	489	SiO ₂	nr		
		Barium	<100	Al ₂ O ₃	nr		
		Bromine	13.3	TiO ₂	nr		
		Cadmium	nr	MnO	nr		
		Caesium	1.87	CaO	nr		
		Calcium (%)	nr	P	nr		
		Cerium	73.4	S	nr		
		Chromium	6420	MgO	nr		
		Cobalt	62.5	K ₂ O	nr		
		Europium	1.03	Na ₂ O	nr		
		Gold (ppb)	4160	LOI1000	nr		
		Hafnium	3.72	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes. 'nr': Not Reported			
		Iridium (ppb)	<20				
		Iron (%)	19.6				
		Lanthanum	15.9				
		Lutetium	0.36				
		Mercury	nr				
		Molybdenum	<5				
		Neodymium	nr				
		Nickel	nr				
		Potassium (%)	<0.2				
		Rubidium	28.2				
		Samarium	4.32				
		Scandium	89				
		Selenium	<5				
		Silver	<5				
		Sodium (%)	0.289				
		Strontium	nr				
		Tantalum	<1				
		Tellurium	nr				
		Terbium	nr				
		Thorium	18.4				
		Tin	nr				
		Tungsten	<4				
		Uranium	6.83				
		Ytterbium	2.84				
		Zinc	<100				
		Zirconium	nr				
Colour Designation (ISCC-NBS, SP440) This material is moderate brown in colour.							
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.							
Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.							
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.							
Stability This product remains stable in its original packaging, away from direct sunlight.							
Material Safety This product is not hazardous and non-toxic.							

20 Hines Road, O'Connor, Western Australia 6163
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699
e-mail : pjh@geostats.com.au, srr@geostats.com.au
Website <http://www.geostats.com.au>

G397-6

Geostats Pty Ltd, Certified Gold Reference Material, Product Code: