

# GEOSTATS PTY LTD


Mining Industry Consultants  
Reference Material Manufacture and Sales

**Certified Gold Reference Material Product Code**

## G397-8

### Certified Control Values

<b>50 gram Fire Assay</b>	
Gold Grade	11.65 ppm
Standard Deviation	0.65 ppm
Confidence Interval	+/- 0.164 ppm
<b>Aqua Regia Digest</b>	
Gold Grade	11.82 ppm
Standard Deviation	0.60 ppm
Confidence Interval	+/- 0.164 ppm



### CRM Details

<b>Control Statistic Details</b>	<b>Neutron Activation Analysis Results (ppm)</b>		<b>Major Elements Fusion / XRF (%)</b>	
	Control statistics were produced from results accumulated in the : <u>April-1997</u> Geostats Pty Ltd Laboratory Round Robin Program. <u>64</u> laboratories tested this material using 50 gram Fire Assay. <u>55</u> laboratories tested it using an Aqua Regia Technique.	Antimony	1.04	Fe
<b>Source Material</b> Prior to homogenisation and testing, this material was sourced from Minor Sulphide in Indonesia.	Arsenic	8.2	SiO2	nr
<b>Colour Designation</b> Very light gray	Barium	<100	Al2O3	nr
<b>Usage</b> This product is for use in the mining industry as reference materials for monitoring and testing the accuracy of laboratory assaying.	Bromine	<2	TiO2	nr
<b>Preparation and Packaging</b> All standards are dried in an oven for a minimum of 12 hours at 110C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an Air Classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	nr	MnO	nr
<b>Assay Testwork</b> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by a minimum of 50 reputable laboratories selected from across the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cerium	6.31	CaO	nr
	Caesium	14.3	P	nr
	Chromium	49.7	S	nr
	Cobalt	9.21	MgO	nr
	Europium	<0.5	K2O	nr
	Gold ppb	12800	Na2O	nr
	Hafnium	4.16	LOI1000	nr
	Iridium ppb	<20		
	Iron %	1.9		
	Lanthanum	2.86		
	Lutetium	<0.2		
	Molybdenum	45.7		
	Nickel	nr		
	Rubidium	436		
	Samarium	1.38		
	Scandium	6.84		
	Selenium	<5		
	Sodium %	1.13		
	Tantalum	<1		
	Tellurium	nr		
	Terbium	nr		
	Thorium	<0.5		
	Tin	nr		
	Tungsten	<4		
	Uranium	<2		
	Ytterbium	0.94		
	Zinc	220		
	Zirconium	nr		
	Calcium%	nr		
	Potassium %	2.04		
	Silver	255		
	Mercury	nr		
	Neodymium	nr		
	Strontium	nr		

10A Marsh Close, O'Connor, Western Australia 6163  
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699  
e-mail : [pjh@geostats.com.au](mailto:pjh@geostats.com.au), [srr@geostats.com.au](mailto:srr@geostats.com.au)  
Website <http://www.geostats.com.au>

G397-8

Geostats Pty Ltd, Certified Gold Reference Material, Product Code :