

# GEOSTATS PTY LTD

Mining Industry Consultants  
Reference Material Manufacture and Sales

**Certified Gold Reference Material Product Code**

## G909-10

### Certified Control Values

**50 gram Fire Assay**

Gold Grade	0.52 ppm
Standard Deviation	0.05 ppm
Confidence Interval	+/- 0.008 ppm

**Aqua Regia Digest**

Gold Grade	0.53 ppm
Standard Deviation	0.07 ppm
Confidence Interval	+/- 0.018 ppm



### CRM Details

<b>Control Statistic Details</b>	<b>Neutron Activation Analysis Results (ppm)</b>		<b>Major Elements Fusion / XRF (%)</b>	
Control statistics were produced from results accumulated in the : <u>October-2009</u> Geostats Pty Ltd Laboratory Round Robin Program. <u>130</u> laboratories tested this material using 50 gram Fire Assay. <u>55</u> laboratories tested it using an Aqua Regia Technique.	Antimony	0.9	Fe	nr
	Arsenic	122	SiO2	nr
	Barium	80	Al2O3	nr
	Bromine	<1	TiO2	nr
	Cadmium	<2	MnO	nr
	Cerium	90	CaO	nr
	Caesium	0.7	P	nr
	Chromium	69	S	nr
	Cobalt	25	MgO	nr
	Europium	0.9	K2O	nr
	Gold ppb	510	Na2O	nr
	Hafnium	13	LOI1000	nr
	Iridium ppb	<20		
	Iron %	1.9		
	Lanthanum	47		
	Lutetium	0.36		
	Molybdenum	<1		
	Nickel	31		
	Rubidium	64		
	Samarium	5.8		
	Scandium	7.4		
	Selenium	<1		
	Sodium %	0.08		
	Tantalum	1.1		
	Tellurium	<10		
	Terbium	0.9		
	Thorium	15		
	Tin	<50		
	Tungsten	56		
	Uranium	3.2		
	Ytterbium	2.8		
	Zinc	<50		
	Zirconium	360		
	Calcium%	nr		
	Potassium %	nr		
	Silver	<1		
	Mercury	nr		
	Neodymium	nr		
	Strontium	nr		
<b>Source Material</b> Prior to homogenisation and testing, this material was sourced from Oxide Ore Low grade Cu / Au				
<b>Colour Designation</b> Yellowish gray				
<b>Usage</b> This product is for use in the mining industry as reference materials for monitoring and testing the accuracy of laboratory assaying.				
<b>Preparation and Packaging</b> All standards are dried in an oven for a minimum of 12 hours at 110C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an Air Classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.				
<b>Assay Testwork</b> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by a minimum of 50 reputable laboratories selected from across the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.				

10A Marsh Close, O'Connor, Western Australia 6163  
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699  
e-mail : [pjh@geostats.com.au](mailto:pjh@geostats.com.au), [srr@geostats.com.au](mailto:srr@geostats.com.au)  
Website <http://www.geostats.com.au>

G909-10

Geostats Pty Ltd, Certified Gold Reference Material, Product Code :