

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Base Metal Reference Material Product Code

GBM303-8


Certified Control Values

Base Metal Analyses

Element	Grade	Standard Deviation	No of Analyses	Confidence Interval
Nickel (ppm)	151	24	57	+/- 6.3
Copper (ppm)	13949	628	66	+/- 155.6
Zinc (ppm)	45	13	56	+/- 3.4
Lead (ppm)	46	11	52	+/- 3.2
Arsenic (ppm)	1152	88	53	+/- 24.4
Cobalt (ppm)	454	46	55	+/- 12.6
Silver (ppm)	7.0	0.8	58	+/- 0.2

CRM Details

Control Statistic Details	Neutron Activation		Major Elements	
	Analysis Results (ppm)		Fusion / XRF (%)	
Control statistics were produced from results accumulated in the : <u>April-2006</u> Geostats Pty Ltd Laboratory Round Robin Program. <u>52</u> laboratories (at least) tested this material for base metal content.	Antimony	1.05	Fe	nr
	Arsenic	1200	SiO ₂	nr
	Barium	144	Al ₂ O ₃	nr
	Bromine	<1	TiO ₂	nr
	Cadmium	nr	MnO	nr
	Cerium	120	CaO	nr
	Caesium	<1	P	nr
	Chromium	34.5	S	nr
	Cobalt	489	MgO	nr
	Europium	1.29	K ₂ O	nr
	Gold ppb	9150	Na ₂ O	nr
	Hafnium	2.43	LOI1000	nr
	Iridium ppb	<20		
	Iron %	19.7		
	Lanthanum	73.9		
	Lutetium	0.27		
	Molybdenum	11.5		
	Nickel	nr		
	Rubidium	<20		
	Samarium	8.53		
	Scandium	10.2		
	Selenium	<5		
	Sodium %	0.305		
	Tantalum	1.34		
	Tellurium	<5		
	Terbium	nr		
	Thorium	5.43		
	Tin	nr		
	Tungsten	398		
	Uranium	2.61		
	Ytterbium	2.22		
	Zinc	<100		
	Zirconium	<500		
	Calcium%	2.34		
	Potassium %	<0.2		
	Silver	9.2		
	Mercury	nr		
	Neodymium	nr		
	Strontium	nr		



Control Statistic Details

Control statistics were produced from results accumulated in the :
April-2006 Geostats Pty Ltd Laboratory Round Robin Program.
52 laboratories (at least) tested this material for base metal content.

Source Material

Prior to homogenisation and testing, this material was sourced from Sulphide Cu / Au Ore Pilbarra

Colour Designation

Dark gray

Usage

This product is for use in the mining industry as reference materials for monitoring and testing the accuracy of laboratory assaying.

Preparation and Packaging

All standards are dried in an oven for a minimum of 12 hours at 110C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an Air Classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.

Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.

Assay Testwork

All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by a minimum of 50 reputable laboratories selected from across the world using a variety of methods (including AR, 3AD, 4AD and ICP, AAS and XRF). Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.

10A Marsh Close, O'Connor, Western Australia 6163
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699
e-mail : pjh@geostats.com.au, srr@geostats.com.au
Website <http://www.geostats.com.au>

GBM303-8

Geostats Pty Ltd, Certified Base Metal Reference Material, Product Code :