

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Ore Grade Base Metal Reference Material Product Code

GBM905-16

Certified Control Values

Ore Grade Base Metal Analyses

Element	Grade	Standard Deviation	No of Analyses	Confidence Interval
Nickel (ppm)	11585	543	42	+/- 171
Copper (ppm)	2405	86	44	+/- 26
Zinc (ppm)	271	42	26	+/- 17
Lead (ppm)	52	44	17	+/- 23
Cobalt (ppm)	nr	nr	nr	nr
Silver (ppm)	nr	nr	nr	nr
Sulphur (%)	nr	nr	nr	nr

CRM Details

Control Statistic Details

Control statistics were produced from results accumulated in the :

October-2005 Geostats Pty Ltd Laboratory Round Robin Program.
17 laboratories (at least) tested this material for base metal content.

Source Material

Prior to homogenisation and testing, this material was sourced from Nickel Sulphide ore

Colour Designation

Medium light gray

Usage

This product is for use in the mining industry as reference materials for monitoring and testing the accuracy of laboratory assaying.

Preparation and Packaging

All standards are dried in an oven for a minimum of 12 hours at 110C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an Air Classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.


Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.

Assay Testwork

All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by a minimum of 50 reputable laboratories selected from across the world using a variety of methods (including AR, 3AD, 4AD and ICP, AAS and XRF). Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.

Neutron Activation Analysis Results (ppm)

Element	Concentration (ppm)	Major Elements Fusion / XRF (%)
Antimony	0.2	Fe nr
Arsenic	10	SiO2 nr
Barium	87	Al2O3 nr
Bromine	2.3	TiO2 nr
Cadmium	<5	MnO nr
Cerium	<5	CaO nr
Caesium	4.3	P nr
Chromium	820	S nr
Cobalt	290	MgO nr
Europium	<1	K2O nr
Gold ppb	93	Na2O nr
Hafnium	<1	LOI1000 nr
Iridium ppb	<50	
Iron %	13	
Lanthanum	<2	
Lutetium	0.2	
Molybdenum	12	
Nickel	11300	
Rubidium	27	
Samarium	1.1	
Scandium	22.5	
Selenium	10	
Sodium %	0.71	
Tantalum	1	
Tellurium	<10	
Terbium	<0.5	
Thorium	0.4	
Tin	<100	
Tungsten	1	
Uranium	<0.2	
Ytterbium	<2	
Zinc	270	
Zirconium	<200	
Calcium%	nr	
Potassium %	nr	
Silver	<2	
Mercury	nr	
Neodymium	nr	
Strontium	nr	



10A Marsh Close, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

GBM905-16

Geostats Pty Ltd, Certified Base Metal Reference Material, Product Code :