

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Base Metal Reference Material Product Code

GBM907-1


Certified Control Values

Base Metal Analyses

Element	Grade	Standard Deviation	No of Analyses	Confidence Interval
Nickel (ppm)	34	8	57	+/- 2.1
Copper (ppm)	1417	67	66	+/- 16.6
Zinc (ppm)	122	16	69	+/- 4
Lead (ppm)	47	7	59	+/- 1.9
Arsenic (ppm)	62	14	54	+/- 3.8
Cobalt (ppm)	78	9	59	+/- 2.2
Silver (ppm)	12.4	0.7	56	+/- 0.2

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm)		Major Elements Fusion / XRF (%)	
	<p>Control statistics were produced from results accumulated in the : <u>October-2007</u> Geostats Pty Ltd Laboratory Round Robin Program. <u>54</u> laboratories (at least) tested this material for base metal content.</p> <p>Source Material Prior to homogenisation and testing, this material was sourced from Low Sulphide free milling ore</p> <p>Colour Designation Light gray</p> <p>Usage This product is for use in the mining industry as reference materials for monitoring and testing the accuracy of laboratory assaying.</p> <p>Preparation and Packaging All standards are dried in an oven for a minimum of 12 hours at 110C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an Air Classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.</p> <p>Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.</p> <p>Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by a minimum of 50 reputable laboratories selected from across the world using a variety of methods (including AR, 3AD, 4AD and ICP, AAS and XRF). Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.</p>	<p>Antimony 0.3</p> <p>Arsenic 64</p> <p>Barium 1600</p> <p>Bromine <0.5</p> <p>Cadmium <5</p> <p>Cerium 140</p> <p>Caesium 1.1</p> <p>Chromium 59</p> <p>Cobalt 90</p> <p>Europium 2</p> <p>Gold ppb 3070</p> <p>Hafnium 7</p> <p>Iridium ppb <50</p> <p>Iron % 6.9</p> <p>Lanthanum 79</p> <p>Lutetium 0.8</p> <p>Molybdenum 23</p> <p>Nickel 42</p> <p>Rubidium 72</p> <p>Samarium 10.3</p> <p>Scandium 18</p> <p>Selenium <5</p> <p>Sodium % 2.17</p> <p>Tantalum 1.4</p> <p>Tellurium <10</p> <p>Terbium 1.4</p> <p>Thorium 24.2</p> <p>Tin <100</p> <p>Tungsten 8</p> <p>Uranium 3.8</p> <p>Ytterbium 5</p> <p>Zinc 140</p> <p>Zirconium 390</p> <p>Calcium% nr</p> <p>Potassium % nr</p> <p>Silver 8</p> <p>Mercury nr</p> <p>Neodymium nr</p> <p>Strontium nr</p>	<p>Fe nr</p> <p>SiO2 nr</p> <p>Al2O3 nr</p> <p>TiO2 nr</p> <p>MnO nr</p> <p>CaO nr</p> <p>P nr</p> <p>S nr</p> <p>MgO nr</p> <p>K2O nr</p> <p>Na2O nr</p> <p>LOI1000 nr</p>	



10A Marsh Close, O'Connor, Western Australia 6163
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699
e-mail : pjh@geostats.com.au, srr@geostats.com.au
Website <http://www.geostats.com.au>

GBM907-1

Geostats Pty Ltd, Certified Base Metal Reference Material, Product Code :