
## **GEOSTATS PTY LTD**

**Mining Industry Consultants Reference Material Manufacture and Sales** 

**Certified Ore Grade Base Metal Reference Material Product Code** 

# **GBM919-13**

### **Certified Control Values**



Major Elements by

Ltd A Pty

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	56	7	81	+/- 2
Copper (ppm)	16692	595	165	+/- 87
Zinc (ppm)	65874	3012	151	+/- 488
Lead (ppm)	3986	182	144	+/- 26
Cobalt (ppm)	nr	nr	nr	nr
Silver (ppm)	17.3	1.1	101	+/- 0.22
Sulphur (%)	5.78	0.20	100	+/- 0.04

### **CRM Details**

Control	Statistic	Dotaile
COLLIO	Statistic	Details

Control statistics were produced from results accumulated in the October-2007. October-2019 round robins. The number of results used to certify each analyte is shown in the table above.

### Material Description

This material is described as a Low grade Copper / Zinc sulphide Ore.

### Colour Designation (ISCC-NBS, SP440)

This material is light gray in colour.

This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.

### Preparation and Packaging

All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.

Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.

### Assay Testwork

All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.

This product remains stable in its original packaging, away from direct sunlight.

### **Material Safety**

This product is not hazardous and non-toxic.

<b>Analysis Resul</b>	Fusion / XRF (%)			
unless otherwi				
Antimony	69.8	Fe	4.62	
Arsenic	404.5	SiO <sub>2</sub>	53.35	
Barium	1850	Al <sub>2</sub> O <sub>3</sub>	11.67	
Bromine	<1.2	TiO <sub>2</sub>	0.47	
Cadmium	337	MnO	0.05	
Caesium	1.3	CaO	2.08	
Calcium (%)	nr	Р	0.092	
Cerium	164	S	5.78	
Chromium	56.5	MgO	1.14	
Cobalt	96.5	K <sub>2</sub> O	3.62	
Europium	1.75	Na <sub>2</sub> O	2.76	
Gold (ppb)	5510	LOI1000	7.35	
Hafnium	7			
Iridium (ppb)	<50	Neutron Act	ivation	
Iron (%)	4.35	Analyses ar	Analyses and Fusion /	
Lanthanum	91	XRF Analyses are		
Lutetium	0.55	single results and are		
Mercury	nr	indicative only. These		
Molybdenum	53.5	are provided for matrix		
Neodymium	nr	identification		
Nickel	60	purposes.		
Potassium (%)	nr			
Rubidium	106.5	'nr': Not Rep	orted	
Samarium	10.95			
Scandium	5.85			
Selenium	<5			
Silver	15.5			
Sodium (%)	1.71			
Strontium	nr			
Tantalum	1.1			
Tellurium	<10			
Terbium	1.15			
Thorium	29.3			
Tin	<100			
Tungsten	8			
Uranium	3.95			
Ytterbium	2.95			
Zinc	66000			
Zirconium	<200			

**Neutron Activation** 

20 Hines Road, O'Connor, Western Australia 6163 Phone: +61 8 9314 2566 | Email: info@geostats.com.au Website: www.geostats.com.au