### **GEOSTATS PTY LTD**

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

# **GBM921-7**

## **Certified Control Values**

#### **Total Digest**

<u> </u>						
Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval		
Nickel (ppm)	42	4	62	+/- 1		
Copper (ppm)	5834	222	69	+/- 53.8		
Zinc (ppm)	9688	328	63	+/- 83.3 +/- 71.9 +/- 7.6		
Lead (ppm)	3048	293	67			
Arsenic (ppm)	346	29	59			
Cobalt (ppm)	42	2	58	+/- 0.5		
Silver (ppm)	19.2	1.0	60	+/- 0.25		

### **Partial Digest**

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval	
Nickel (ppm)	27	3	54	+/- 0.9	
Copper (ppm)	5878	197	86	+/- 42.5	
Zinc (ppm)	9890	460	64	+/- 115.8 +/- 53.6	
Lead (ppm)	3158	226	72		
Arsenic (ppm)	351	33	65	+/- 8.4	
Cobalt (ppm)	29	3	63	+/- 0.8	
Silver (ppm)	19.2	1.0	78	+/- 0.23	

#### **CRM Details**

	Neutron Activation Analysis Results (ppm,		Major Eler	Major Elements by	
Control Statistic Details			Fusion / XRF (%)		
Control statistics were produced from results accumulated in the October-2021	unless otherwi	se noted)			
round robin. The number of results used to certify each analyte is shown in the	Antimony	116	Fe	6.3	
table above.	Arsenic	360	SiO <sub>2</sub>	57.13	
	Barium	325	Al <sub>2</sub> O <sub>3</sub>	13.84	
Material Description	Bromine	<2	TiO <sub>2</sub>	1.173	
This material is described as a Low Cu Pb Zn .	Cadmium	21.9	MnO	0.13	
	Caesium	2	CaO	6.01	
	Calcium (%)	nr	P	0.06	
Colour Designation (ISCC-NBS, SP440)	Cerium	37	S	1.13	
This material is med. light gray in colour.	Chromium	110	MgO	3.55	
	Cobalt	44.5	K <sub>2</sub> O	1.89	
<u>Usage</u>	Europium	1.1	Na <sub>2</sub> O	3.181	
This product is for use in the mining industry as a reference material for	Gold (ppb)	481	LOI1000	1.17	
monitoring and testing the accuracy of laboratory assaying.	Hafnium	<5			
	Iridium (ppb)	<50	Neutron Act	ivation	
Preparation and Packaging	Iron (%)	6.6	Analyses an	d Fusion /	
All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry	Lanthanum	19	XRF Analys	es are	
material is then pulverised to better than 75 micron (nominal mean of 45	Lutetium	0.4	single results and are		
micron) using an air classifier. The material is then homogenised and stored in	Mercury	nr	Ŭ		
a sealed, stable container ready for final packaging.	Molybdenum	53	indicative or	•	
	Neodymium	nr	are provided	d for matrix	
Materials are statistically sampled from stores, then packaged into either heat	Nickel	57	identification	n purposes.	
sealed, air tight, plastic pulp packets or screw top sealed plastic containers	Potassium (%)	nr			
ready for distribution. All packaging has been chosen to ensure minimal	Rubidium	80	'nr': Not Rep	orted	
contamination from outside sources during shipment, use and storage.	Samarium	4.5			
	Scandium	20.9			
Assay Testwork	Selenium	<10			
All standards are tested thoroughly in the Geostats bi-annual laboratory survey.	Silver	20			
This involves assaying by multiple laboratories from around the world. Results	Sodium (%)	2.35			
are compiled into a comprehensive report detailing statistics for each standard.	Strontium	nr			
Assay distributions are checked and processed statistically, producing	Tantalum	<2			
monitoring statistics for these standards. Materials are tested regularly to	Tellurium	<20			
ensure stability and homogeneity.	Terbium	1			
	Thorium	11.1			
<u>Stability</u>	Tin	<200			
This product remains stable in its original packaging, away from direct sunlight.	Tungsten	<2			
	Uranium	6			
Material Safety	Ytterbium	2.7			
This product is not hazardous and non-toxic.	Zinc	10200			
	Zirconium	<500			

20 Hines Road, O'Connor, Western Australia 6163 Phone: +61 8 9314 2566 | Email: info@geostats.com.au Website: www.geostats.com.au