


GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Ore Grade Base Metal Reference Material Product Code

GBM922-14

Certified Control Values



Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	41	9	97	+/- 2
Copper (ppm)	28331	1005	227	+/- 132
Zinc (ppm)	949	71	213	+/- 10
Lead (ppm)	165	21	114	+/- 4
Cobalt (ppm)	nr	nr	nr	nr
Silver (ppm)	8.9	0.9	214	+/- 0.12
Sulphur (%)	3.51	0.17	176	+/- 0.03

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)	Major Elements by Fusion / XRF (%)
Control statistics were produced from results accumulated in the October-2022, October-2012 round robins. The number of results used to certify each analyte is shown in the table above.	Antimony 7.4 Arsenic 58 Barium 269 Bromine <2 Cadmium <10 Caesium 2 Calcium (%) nr Cerium 34 Chromium 90 Cobalt 82 Europium 1.1 Gold (ppb) 2300 Hafnium 6 Iridium (ppb) <50 Iron (%) 9.1 Lanthanum 19 Lutetium 0.4 Mercury nr Molybdenum 127 Neodymium nr Nickel <100 Potassium (%) nr Rubidium 5.7 Samarium 4.6 Scandium 20.7 Selenium 12 Silver 8 Sodium (%) 2.13 Strontium nr Tantalum <2 Tellurium <20 Terbium <1 Thorium 8.7 Tin <200 Tungsten <2 Uranium 6 Ytterbium 2.7 Zinc 950 Zirconium <500	Fe 8.76 SiO ₂ 53.47 Al ₂ O ₃ 12.85 TiO ₂ 1.271 MnO 0.12 CaO 6.04 P 0.066 S 3.56 MgO 3.27 K ₂ O 1.58 Na ₂ O 2.927 LOI1000 1.81 Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes. 'nr': Not Reported
Material Description This material is described as a Cu Pb Zn Ore.		
Colour Designation (ISCC-NBS, SP440) This material is medium gray in colour.		
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.		
Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.		
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.		
Stability This product remains stable in its original packaging, away from direct sunlight.		
Material Safety This product is not hazardous and non-toxic.		

20 Hines Road, O'Connor, Western Australia 6163
Phone: +61 8 9314 2566 | Email: info@geostats.com.au
Website: www.geostats.com.au

GBM922-14

Geostats Pty Ltd, Certified Ore Grade Base Metal Reference Material, Product Code: