

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Base Metal Reference Material Product Code

GBM999-1


Certified Control Values

Base Metal Analyses

Element	Grade	Standard Deviation	No of Analyses	Confidence Interval
Nickel (ppm)	11728	701	56	+/- 189.4
Copper (ppm)	435	34	71	+/- 8.1
Zinc (ppm)	53	14	64	+/- 3.5
Lead (ppm)	13	10	41	+/- 3.2
Arsenic (ppm)	8	4	30	+/- 1.5
Cobalt (ppm)	297	29	58	+/- 7.7
Silver (ppm)	0.8	0.5	22	+/- 0.2

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm)		Major Elements Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the : <u>October-1999</u> Geostats Pty Ltd Laboratory Round Robin Program. <u>22</u> laboratories (at least) tested this material for base metal content.	Antimony	0.39	Fe
Source Material Prior to homogenisation and testing, this material was sourced from Yilgarn Nickel Sulphide Ore	Arsenic	7.63	SiO ₂	nr
	Barium	<100	Al ₂ O ₃	nr
Colour Designation Medium gray	Bromine	3.69	TiO ₂	nr
	Cadmium	nr	MnO	nr
Usage This product is for use in the mining industry as reference materials for monitoring and testing the accuracy of laboratory assaying.	Cerium	2.84	CaO	nr
	Caesium	<1	P	nr
Preparation and Packaging All standards are dried in an oven for a minimum of 12 hours at 110C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an Air Classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Chromium	1010	S	nr
	Cobalt	315	MgO	nr
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by a minimum of 50 reputable laboratories selected from across the world using a variety of methods (including AR, 3AD, 4AD and ICP, AAS and XRF). Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Europium	<0.5	K ₂ O	nr
	Gold ppb	<5	Na ₂ O	nr
	Hafnium	<0.5	LOI1000	nr
	Iridium ppb	<20		
	Iron %	11		
	Lanthanum	0.53		
	Lutetium	<0.2		
	Molybdenum	<5		
	Nickel	nr		
	Rubidium	<20		
	Samarium	0.27		
	Scandium	5.61		
	Selenium	<5		
	Sodium %	0.047		
	Tantalum	<1		
	Tellurium	<5		
	Terbium	nr		
	Thorium	<0.5		
	Tin	nr		
	Tungsten	<2		
	Uranium	<2		
	Ytterbium	<0.5		
	Zinc	<100		
	Zirconium	<500		
	Calcium%	1.76		
	Potassium %	<0.2		
	Silver	<5		
	Mercury	nr		
	Neodymium	nr		
	Strontium	nr		



10A Marsh Close, O'Connor, Western Australia 6163
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699
e-mail : pjh@geostats.com.au, srr@geostats.com.au
Website <http://www.geostats.com.au>

GBM999-1

Geostats Pty Ltd, Certified Base Metal Reference Material, Product Code :