

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales


Certified Low Level Gold Reference Material Product Code

GLG305-2

Certified Control Values

Low Level Gold

Gold Grade 191.23 ppb
Standard Deviation 21.27 ppb
Confidence Interval +/- 6.71 ppb



CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	Control statistics were produced from results accumulated in the April-2005 round robin. A total of 42 gold assays were used to certify this material.	Antimony	0.699	Fe
<u>Material Description</u> This material is described as a Composite soil /cap material ex eastern Goldfields.	Arsenic	<0.56	SiO ₂	nr
	Barium	58	Al ₂ O ₃	nr
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is light brownish gray in colour.	Bromine	<0.5	TiO ₂	nr
	Cadmium	<4	MnO	nr
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Caesium	32.4	CaO	nr
	Calcium (%)	nr	P	nr
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cerium	11	S	nr
	Chromium	79.8	MgO	nr
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cobalt	16.3	K ₂ O	nr
	Europium	0.834	NazO	nr
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Gold (ppb)	220	LOI1000	nr
	Hafnium	1.9		
<u>Material Safety</u> This product is not hazardous and non-toxic.	Iridium (ppb)	<3.8	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
	Iron (%)	3.75	nr: Not Reported	
	Lanthanum	4.52		
	Lutetium	0.22		
	Mercury	<0.1		
	Molybdenum	<1.5		
	Neodymium	6		
	Nickel	<47		
	Potassium (%)	3.2		
	Rubidium	986		
	Samarium	2.21		
	Scandium	13.6		
	Selenium	<0.9		
	Silver	1.1		
	Sodium (%)	1.48		
	Strontium	nr		
	Tantalum	0.354		
	Tellurium	<2.9		
	Terbium	0.32		
	Thorium	0.595		
	Tin	<58		
	Tungsten	<1.2		
	Uranium	0.35		
	Ytterbium	1.37		
	Zinc	38.9		
	Zirconium	<120		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

GLG305-2

Geostats Pty Ltd, Certified Low Level Gold Reference Material, Product Code: