Major Elements by

# **GEOSTATS PTY LTD**

Mining Industry Consultants
Reference Material Manufacture and Sales

#### **Certified Low Level Gold Reference Material Product Code**

# **GLG321-1**

## **Certified Control Values**

## **Low Level Gold**

Gold Grade 24.31 ppb

Standard Deviation 4.50 ppb

Confidence Interval +/- 1.02 ppb

**Control Statistic Details** 

This product is not hazardous and non-toxic.



**Neutron Activation** 

Analysis Results (ppm, Fusion / XRF (%)

#### **CRM Details**

	:			( / -/
Control statistics were produced from results accumulated in the April-2021	unless otherwi	unless otherwise noted)		
round robin. A total of 78 gold assays were used to certify this material.	Antimony	2.5	Fe	4.69
	Arsenic	56.4	SiO <sub>2</sub>	61.35
	Barium	189	Al <sub>2</sub> O <sub>3</sub>	14.47
Material Description	Bromine	<2	TiO <sub>2</sub>	0.66
This material is described as a Fresh andesite, Pilbara, WA.	Cadmium	<10	MnO	0.08
	Caesium	3	CaO	3.15
	Calcium (%)	nr	Р	0.066
Colour Designation (ISCC-NBS, SP440)	Cerium	41	S	0.71
This material is very light gray in colour.	Chromium	52	MgO	2.99
	Cobalt	18	K <sub>2</sub> O	2.3
Usage	Europium	0.9	Na <sub>2</sub> O	1.63
This product is for use in the mining industry as a reference material for	Gold (ppb)	25	LOI1000	6.04
monitoring and testing the accuracy of laboratory assaying.	Hafnium	<5		
	Iridium (ppb)	<50	Neutron Act	ivation
Preparation and Packaging	Iron (%)	4.8	Analyses an	nd Fusion /
All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry	Lanthanum	21	XRF Analyses are	
material is then pulverised to better than 75 micron (nominal mean of 45 micron)	Lutetium	0.3		
using an air classifier. The material is then homogenised and stored in a sealed,	Mercury	nr	single results and are	
stable container ready for final packaging.	Molybdenum	<10	indicative only. These	
	Neodymium	nr	are provided for matrix	
Materials are statistically sampled from stores, then packaged into either heat	Nickel	33	identification purposes.	
sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready	Potassium (%)	nr		
for distribution. All packaging has been chosen to ensure minimal contamination	Rubidium	88	'nr': Not Reported	
from outside sources during shipment, use and storage.	Samarium	3.5	•	
	Scandium	11.2		
Assay Testwork	Selenium	<10		
All standards are tested thoroughly in the Geostats bi-annual laboratory survey.	Silver	<5		
This involves assaying by multiple laboratories from around the world. Results	Sodium (%)	1.14		
are compiled into a comprehensive report detailing statistics for each standard.	Strontium	nr		
Assay distributions are checked and processed statistically, producing	Tantalum	<2		
monitoring statistics for these standards. Materials are tested regularly to ensure	Tellurium	<20		
stability and homogeneity.	Terbium	1		
	Thorium	4.56		
Stability	Tin	<200		
This product remains stable in its original packaging, away from direct sunlight.	Tungsten	3		
	Uranium	<2		
Material Safety	Ytterbium	1.8		
<del></del>	<b></b>			

20 Hines Road, O'Connor, Western Australia 6163
Phone: +61 8 9314 2566 | Email: info@geostats.com.au
Website: www.geostats.com.au

Zinc

Zirconium

<200

<500