**Major Elements by** 

# **GEOSTATS PTY LTD**

Mining Industry Consultants
Reference Material Manufacture and Sales

**Certified Low Level Gold Reference Material Product Code** 

**GLG322-4** 

### **Certified Control Values**

#### **Low Level Gold**

Gold Grade 10.96 ppb

Standard Deviation 3.95 ppb

Confidence Interval +/- 0.65 ppb



**Neutron Activation** 

#### **CRM Details**

# Control Statistic Details

Control statistics were produced from results accumulated in the April-2022, April-2006, October-2002 round robins. A total of 145 gold assays were used to certify this material.

### Material Description

This material is described as a Calcrete Material (carbonate).

### Colour Designation (ISCC-NBS, SP440)

This material is white in colour.

### <u>Usage</u>

This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.

### Preparation and Packaging

All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.

Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.

#### **Assay Testwork**

All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.

## **Stability**

This product remains stable in its original packaging, away from direct sunlight.

#### <u>Material Safety</u>

This product is not hazardous and non-toxic.

Analysis Results (ppm,		Fusion / XRF (%)		
unless otherwi	se noted)			
Antimony	<0.2	Fe	0.07	
Arsenic	0.5	SiO <sub>2</sub>	26.94	
Barium	<50	Al <sub>2</sub> O <sub>3</sub>	3.27	
Bromine	<2	TiO <sub>2</sub>	0.02	
Cadmium	<10	MnO	<0.01	
Caesium	11	CaO	36.44	
Calcium (%)	nr	Р	0.027	
Cerium	<5	S	0.73	
Chromium	10	MgO	0.96	
Cobalt	<5	K <sub>2</sub> O	1.98	
Europium	<0.5	Na <sub>2</sub> O	0.69	
Gold (ppb)	11	LOI1000	29.2	
Hafnium	5			
Iridium (ppb)	<50	Neutron Activation		
Iron (%)	<0.2	Analyses an	yses and Fusion /	
Lanthanum	<2	XRF Analyses are		
Lutetium	<0.2	single results and are		
Mercury	nr			
Molybdenum	<10	indicative only. These		
Neodymium	nr	are provided for matrix		
Nickel	<20	identification purposes		
Potassium (%)	nr			
Rubidium	383	'nr': Not Rep	orted	
Samarium	<0.2			
Scandium	<0.2			
Selenium	<10			
Silver	<5			
Sodium (%)	0.47			
Strontium	nr			
Tantalum	<2			
Tellurium	<20			
Terbium	<1			
Thorium	<0.5			
Tin	<200			
Tungsten	<2			
Uranium	1			
Ytterbium	<0.5			
Zinc	<200			
Zirconium	<b>~</b> 500	1		

20 Hines Road, O'Connor, Western Australia 6163
Phone: +61 8 9314 2566 | Email: info@geostats.com.au
Website: www.geostats.com.au