

# GEOSTATS PTY LTD

Mining Industry Consultants  
Reference Material Manufacture and Sales


## Certified Low Level Gold Reference Material Product Code

# GLG904-1

### Certified Control Values

#### Low Level Gold

Gold Grade	3.82 ppb
Standard Deviation	2.25 ppb
Confidence Interval	+/- 0.52 ppb



### CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	Control statistics were produced from results accumulated in the October-2004 & April-2011 round robins. A total of 75 gold assays were used to certify this material.	Antimony	0.1	Fe
<u>Material Description</u> This material is described as a Low grade Au Pt Pd Material.	Arsenic	0.618	SiO <sub>2</sub>	67.24
	Barium	67.9	Al <sub>2</sub> O <sub>3</sub>	11.77
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is light gray in colour.	Bromine	0.396	TiO <sub>2</sub>	1.015
	Cadmium	<5	MnO	0.09
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Caesium	32.05	CaO	4.82
	Calcium (%)	nr	P	0.072
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cerium	10.85	S	0.02
	Chromium	95.5	MgO	2.72
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cobalt	22.55	K <sub>2</sub> O	3.05
	Europium	0.646	NazO	2.157
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Gold (ppb)	3	LOI1000	0.26
	Hafnium	1.425	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
<u>Material Safety</u> This product is not hazardous and non-toxic.	Iridium (ppb)	<20	'nr': Not Reported	
	Iron (%)	4.225		
	Lanthanum	5.235		
	Lutetium	0.2		
	Mercury	nr		
	Molybdenum	<1		
	Neodymium	nr		
	Nickel	20.2		
	Potassium (%)	nr		
	Rubidium	917		
	Samarium	2.735		
	Scandium	16.85		
	Selenium	<5		
	Silver	<2		
	Sodium (%)	1.465		
	Strontium	nr		
	Tantalum	0.39		
	Tellurium	<5		
	Terbium	0.643		
	Thorium	0.816		
	Tin	<100		
	Tungsten	<1		
	Uranium	0.171		
	Ytterbium	1.91		
	Zinc	61.9		
	Zirconium	<200		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

GLG904-1

Geostats Pty Ltd, Certified Low Level Gold Reference Material, Product Code: