GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Low Level Gold Reference Material Product Code

GLG919-1

Certified Control Values

Low Level Gold

Gold Grade 120.71 ppb

Standard Deviation 8.49 ppb

Confidence Interval +/- 1.43 ppb



CRM Details

Control Statistic Details Control statistics were produced from results accumulated in the April-2010, October-2019 round robins. A total of 138 gold assays were used to certify this material. Material Description This material is described as a Milled Tail sample low sulphide. Cadmiun Calcium Colour Designation (ISCC-NBS, SP440) This material is light gray in colour. Cobalt Usage This product is for use in the mining industry as a reference material for Gold (pp

Preparation and Packaging

All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.

monitoring and testing the accuracy of laboratory assaying.

Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.

Assay Testwork

All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.

Stability

This product remains stable in its original packaging, away from direct sunlight.

<u>Material Safety</u>

This product is not hazardous and non-toxic.

Neutron Activation		Major Elements by		
Analysis Results (ppm,		Fusion / XRF (%)		
unless otherwise noted)				
Antimony	0.1	Fe	7.77	
Arsenic	<0.5	SiO ₂	55.27	
Barium	263	Al ₂ O ₃	14.29	
Bromine	<0.5	TiO ₂	2.1	
Cadmium	<5	MnO	0.15	
Caesium	1	CaO	7.77	
Calcium (%)	nr	Р	0.08	
Cerium	35.55	S	0.07	
Chromium	120.5	MgO	4.41	
Cobalt	33.75	K ₂ O	1.2	
Europium	1.615	Na ₂ O	3.11	
Gold (ppb)	127.5	LOI1000	0.41	
Hafnium	5.09			
Iridium (ppb)	<5	Neutron Act	eutron Activation	
Iron (%)	7.69	Analyses and Fusion /		
Lanthanum	15.85	XRF Analyses are		
Lutetium	0.498	single results and are		
Mercury	nr			
Molybdenum	6	indicative only. These		
Neodymium	nr	are provided for matrix		
Nickel	34	identification purposes.		
Potassium (%)	nr			
Rubidium	55	'nr': Not Rep	orted	
Samarium	5.06			
Scandium	28.75			
Selenium	<1.5			
Silver	<1.9			
Sodium (%)	2.225			
Strontium	nr			
Tantalum	1.755			
Tellurium	<3.9			
Terbium	1			
Thorium	6.525			
Tin	<100			
Tungsten	1			
Uranium	3.15			
Ytterbium	3.15			
Zinc	124			
Zirconium	<500			

20 Hines Road, O'Connor, Western Australia 6163
Phone: +61 8 9314 2566 | Email: info@geostats.com.au
Website: www.geostats.com.au