

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Gold Reference Material Product Code

G924-1


Certified Control Values

50 gram Fire Assay

Gold Grade 0.54 ppm
Standard Deviation 0.04 ppm
Confidence Interval +/- 0.007 ppm

Aqua Regia Digest

Gold Grade 0.49 ppm
Standard Deviation 0.05 ppm
Confidence Interval +/- 0.014 ppm



CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the October-2024 round robin. A total of 169 fire assay results and 52 results from an aqua regia technique were used to certify this material.	Antimony	10.9	Fe
Material Description This material is described as a Stream sediments, Pilbara, WA.	Arsenic	333	SiO ₂	63.32
	Barium	253	Al ₂ O ₃	12.43
Colour Designation (ISCC-NBS, SP440) This material is light brown in colour.	Bromine	<2	TiO ₂	0.62
	Cadmium	<10	MnO	0.1
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Caesium	3	CaO	3.75
	Calcium (%)	nr	P	0.034
Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cerium	26	S	0.04
	Chromium	193	MgO	2.9
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cobalt	26	K ₂ O	1.64
	Europium	0.7	Na ₂ O	0.94
Stability This product remains stable in its original packaging, away from direct sunlight.	Gold (ppb)	540	LOI1000	4.97
	Hafnium	<5	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
Material Safety This product is not hazardous and non-toxic.	Iridium (ppb)	<50	'nr': Not Reported	
	Iron (%)	6.2		
	Lanthanum	13		
	Lutetium	0.2		
	Mercury	nr		
	Molybdenum	<10		
	Neodymium	nr		
	Nickel	<100		
	Potassium (%)	nr		
	Rubidium	72		
	Samarium	2.5		
	Scandium	15.6		
	Selenium	<10		
	Silver	<5		
	Sodium (%)	0.65		
	Strontium	nr		
	Tantalum	<2		
	Tellurium	<20		
	Terbium	<1		
	Thorium	4.9		
	Tin	<200		
	Tungsten	3		
	Uranium	1		
	Ytterbium	1.5		
	Zinc	<200		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163
Phone: +61 8 9314 2566 | Email: info@geostats.com.au
Website: www.geostats.com.au

G924-1

Geostats Pty Ltd, Certified Gold Reference Material, Product Code: