


GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Ore Grade Base Metal Reference Material Product Code

GBM324-13

Certified Control Values



GBM324-13

Geostats Pty Ltd, Certified Ore Grade Base Metal Reference Material, Product Code:

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	38775	1744	160	+/- 273
Copper (ppm)	48	7	165	+/- 1
Zinc (ppm)	66	30	142	+/- 5
Lead (ppm)	17	13	110	+/- 2
Cobalt (ppm)	nr	nr	nr	nr
Silver (ppm)	4.6	0.5	171	+/- 0.07
Sulphur (%)	0.05	0.01	143	+/- 0

CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>	<u>Major Elements by Fusion / XRF (%)</u>	
Control statistics were produced from results accumulated in the April-2020, April-2024 round robins. The number of results used to certify each analyte is shown in the table above.	Antimony <0.2	Fe	4.19
	Arsenic 6	SiO ₂	63.36
	Barium <100	Al ₂ O ₃	12.14
	Bromine <2	TiO ₂	0.94
	Cadmium <10	MnO	0.08
	Caesium 20	CaO	4.55
	Calcium (%) nr	P	0.07
	Cerium 13	S	0.04
	Chromium 150	MgO	2.73
	Cobalt 60	K ₂ O	3.4
	Europium 0.8	Na ₂ O	2.34
	Gold (ppb) 871	LOI1000	-0.66
	Hafnium <5	Neutron Activation	
	Iridium (ppb) <50	Analyses and Fusion /	
	Iron (%) 4.6	XRF Analyses are	
	Lanthanum 5	single results and are	
	Lutetium 0.2	indicative only. These	
	Mercury nr	are provided for matrix	
	Molybdenum <10	identification	
	Neodymium nr	purposes.	
	Nickel 40100	'nr': Not Reported	
	Potassium (%) nr		
	Rubidium 727		
	Samarium 2.6		
	Scandium 16.7		
	Selenium <10		
	Silver 5		
	Sodium (%) 1.73		
	Strontium nr		
	Tantalum <2		
	Tellurium <20		
	Terbium <1		
	Thorium 1		
	Tin <200		
	Tungsten <2		
	Uranium <1		
	Ytterbium 1.6		
	Zinc <200		
	Zirconium <500		
<u>Material Description</u> This material is described as an Oxide Cap Rock.			
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is light gray in colour.			
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.			
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.			
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.			
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.			
<u>Material Safety</u> This product is not hazardous and non-toxic.			

20 Hines Road, O'Connor, Western Australia 6163

Phone: +61 8 9314 2566 | Email: info@geostats.com.au

Website: www.geostats.com.au