

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

GBM326-9



Certified Control Values

Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	14	2	51	+/- 0.5
Copper (ppm)	154	10	60	+/- 2.7
Zinc (ppm)	67	6	54	+/- 1.6
Lead (ppm)	119	11	50	+/- 3.2
Arsenic (ppm)	5	nr	nr	nr
Cobalt (ppm)	8	1	46	+/- 0.2
Silver (ppm)	2.7	0.2	47	+/- 0.06

Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	11	1	42	+/- 0.3
Copper (ppm)	157	10	71	+/- 2.4
Zinc (ppm)	56	6	56	+/- 1.5
Lead (ppm)	110	8	55	+/- 2.2
Arsenic (ppm)	6	1	37	+/- 0.5
Cobalt (ppm)	5	1	39	+/- 0.2
Silver (ppm)	2.7	0.2	58	+/- 0.06

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the April-2026 round robin. The number of results used to certify each analyte is shown in the table above.	Antimony	4.7	Fe
Material Description This material is described as an Oxide cut off ore.	Arsenic	6	SiO ₂	67.66
	Colour Designation (ISCC-NBS, SP440) This material is pale red in colour.	Barium	634	Al ₂ O ₃
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.		Bromine	2	TiO ₂
	Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	<10	MnO
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.		Caesium	5	CaO
	Stability This product remains stable in its original packaging, away from direct sunlight.	Calcium (%)	nr	P
Material Safety This product is not hazardous and non-toxic.		Cerium	52	S
	Neutron Activation Analysis Results (ppm, unless otherwise noted)	Chromium	17	MgO
Major Elements by Fusion / XRF (%)		Cobalt	9	K ₂ O
	Antimony	Europium	1.2	Na ₂ O
Arsenic		Gold (ppb)	1440	LOH1000
	Barium	Hafnium	7	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.
Bromine		Iridium (ppb)	<50	"nr": Not Reported
	Cadmium	Iron (%)	2.8	
Caesium		Lanthanum	31	
	Calcium (%)	Lutetium	0.4	
Cerium		Mercury	nr	
	Chromium	Molybdenum	<10	
Cobalt		Neodymium	nr	
	Europium	Nickel	<100	
Gold (ppb)		Potassium (%)	nr	
	Hafnium	Rubidium	189	
Iridium (ppb)		Samarium	4.01	
	Iron (%)	Scandium	7.3	
Lanthanum		Selenium	<10	
	Lutetium	Silver	<5	
Mercury		Sodium (%)	2.92	
	Molybdenum	Strontium	nr	
Neodymium		Tantalum	2	
	Nickel	Tellurium	<20	
Potassium (%)		Terbium	<1	
	Rubidium	Thorium	24.8	
Samarium		Tin	<200	
	Scandium	Tungsten	2	
Selenium		Uranium	13	
	Silver	Ytterbium	2.6	
Sodium (%)		Zinc	<200	
	Strontium	Zirconium	<500	
Tantalum				
	Tellurium			
Terbium				
	Thorium			
Tin				
	Tungsten			
Uranium				
	Ytterbium			
Zinc				
	Zirconium			

20 Hines Road, O'Connor, Western Australia 6163

Phone: +61 8 9314 2566 | Email: info@geostats.com.au

Website: www.geostats.com.au

GBM326-9

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: