

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

GBM924-5



Certified Control Values

Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	52	4	58	+/- 1.1
Copper (ppm)	2697	122	67	+/- 30
Zinc (ppm)	75	4	50	+/- 1.1
Lead (ppm)	10	2	46	+/- 0.6
Arsenic (ppm)	10	2	40	+/- 0.6
Cobalt (ppm)	18	1	53	+/- 0.3
Silver (ppm)	1.9	0.2	45	+/- 0.06

Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	45	3	49	+/- 0.8
Copper (ppm)	2720	108	81	+/- 24.1
Zinc (ppm)	67	4	59	+/- 1.2
Lead (ppm)	7	2	54	+/- 0.5
Arsenic (ppm)	9	1	47	+/- 0.4
Cobalt (ppm)	14	1	47	+/- 0.3
Silver (ppm)	1.8	0.1	56	+/- 0.03

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the October-2024 round robin. The number of results used to certify each analyte is shown in the table above.	Antimony	0.3	Fe
Material Description This material is described as an Archean porphyry-style Cu/Au/Mo.	Arsenic	9	SiO ₂	63.55
	Colour Designation (ISCC-NBS, SP440) This material is light gray in colour.	Barium	268	Al ₂ O ₃
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.		Bromine	<2	TiO ₂
	Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	<10	MnO
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.		Caesium	7	CaO
	Stability This product remains stable in its original packaging, away from direct sunlight.	Calcium (%)	nr	P
Material Safety This product is not hazardous and non-toxic.		Cerium	33	S
	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	Chromium	189	MgO
'nr': Not Reported		Cobalt	18	K ₂ O
	Europium	0.6	Na ₂ O	3.53
Gold (ppb)	914	LOH1000	0.87	
Hafnium	<5			
Iridium (ppb)	<50			
Iron (%)	4.1			
Lanthanum	19			
Lutetium	0.2			
Mercury	nr			
Molybdenum	43			
Neodymium	nr			
Nickel	<100			
Potassium (%)	nr			
Rubidium	184			
Samarium	2.8			
Scandium	11.9			
Selenium	<10			
Silver	<5			
Sodium (%)	2.43			
Strontium	nr			
Tantalum	<2			
Tellurium	<20			
Terbium	<1			
Thorium	6.6			
Tin	<200			
Tungsten	37			
Uranium	4			
Ytterbium	1			
Zinc	<200			
Zirconium	<500			

20 Hines Road, O'Connor, Western Australia 6163

Phone: +61 8 9314 2566 | Email: info@geostats.com.au

Website: www.geostats.com.au

GBM924-5

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: