

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

GBM924-6



Certified Control Values

Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	16	2	53	+/- 0.7
Copper (ppm)	24	5	59	+/- 1.3
Zinc (ppm)	35	6	58	+/- 1.5
Lead (ppm)	29	4	51	+/- 1.1
Arsenic (ppm)	10	2	41	+/- 0.7
Cobalt (ppm)	8	1	51	+/- 0.4
Silver (ppm)	0.4	nr	nr	nr

Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	11	1	49	+/- 0.4
Copper (ppm)	20	3	72	+/- 0.6
Zinc (ppm)	24	5	58	+/- 1.3
Lead (ppm)	21	4	59	+/- 1
Arsenic (ppm)	5	1	40	+/- 0.5
Cobalt (ppm)	5	1	49	+/- 0.4
Silver (ppm)	0.2	nr	nr	nr

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the October-2024 round robin. The number of results used to certify each analyte is shown in the table above.	Antimony	1.3	Fe
Material Description This material is described as a Milled Oxide material.	Arsenic	10	SiO ₂	49.03
	Colour Designation (ISCC-NBS, SP440) This material is pale reddish brown in colour.	Barium	374	Al ₂ O ₃
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.		Bromine	3	TiO ₂
	Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	<10	MnO
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.		Caesium	3	CaO
	Stability This product remains stable in its original packaging, away from direct sunlight.	Calcium (%)	nr	P
Material Safety This product is not hazardous and non-toxic.		Cerium	36	S
	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	Chromium	95	MgO
'nr': Not Reported		Cobalt	9	K ₂ O
	Europium	0.5	Na ₂ O	2.26
Iridium (ppb)	7	LOH1000	7.66	
	Iron (%)	<50		
Lanthanum	8.3			
Lutetium	18			
Mercury	0.2			
Molybdenum	nr			
Neodymium	<10			
Nickel	nr			
Potassium (%)	<100			
Rubidium	nr			
Samarium	101			
Scandium	2.3			
Selenium	12.7			
Silver	<10			
Sodium (%)	<5			
Strontium	1.57			
Tantalum	nr			
Tellurium	3			
Terbium	<20			
Thorium	<1			
Tin	47.5			
Tungsten	<200			
Uranium	2			
Ytterbium	9			
Zinc	1.3			
Zirconium	<200			
	<500			

20 Hines Road, O'Connor, Western Australia 6163

Phone: +61 8 9314 2566 | Email: info@geostats.com.au

Website: www.geostats.com.au

GBM924-6

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: