


# GEOSTATS PTY LTD

Mining Industry Consultants  
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

## GBM924-7



### Certified Control Values

#### Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	163	11	64	+/- 2.8
Copper (ppm)	289	18	65	+/- 4.4
Zinc (ppm)	353	23	62	+/- 6
Lead (ppm)	268	24	57	+/- 6.5
Arsenic (ppm)	353	34	55	+/- 9.2
Cobalt (ppm)	332	21	62	+/- 5.4
Silver (ppm)	1.9	0.2	47	+/- 0.05

#### Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	162	14	57	+/- 3.8
Copper (ppm)	293	16	82	+/- 3.6
Zinc (ppm)	333	25	68	+/- 6
Lead (ppm)	265	15	60	+/- 4
Arsenic (ppm)	358	30	62	+/- 7.6
Cobalt (ppm)	329	19	54	+/- 5.3
Silver (ppm)	1.9	0.1	52	+/- 0.03

### CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the October-2024 round robin. The number of results used to certify each analyte is shown in the table above.	Antimony	11.2	Fe
<b>Material Description</b> This material is described as an Oxide milled mine waste.	Arsenic	355	SiO <sub>2</sub>	68.15
	Barium	551	Al <sub>2</sub> O <sub>3</sub>	13.16
<b>Colour Designation (ISCC-NBS, SP440)</b> This material is pale red in colour.	Bromine	<2	TiO <sub>2</sub>	0.711
	Cadmium	<10	MnO	0.07
<b>Usage</b> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Caesium	5	CaO	3.39
	Calcium (%)	nr	P	0.041
<b>Preparation and Packaging</b> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cerium	45	S	0.1
	Chromium	48	MgO	1.66
<b>Assay Testwork</b> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cobalt	335	K <sub>2</sub> O	2.96
	Europium	0.8	Na <sub>2</sub> O	3.397
<b>Stability</b> This product remains stable in its original packaging, away from direct sunlight.	Gold (ppb)	63	LOH1000	0.58
	Hafnium	<5	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
<b>Material Safety</b> This product is not hazardous and non-toxic.	Iridium (ppb)	<50	'nr': Not Reported	
	Iron (%)	3.4		
	Lanthanum	27		
	Lutetium	0.3		
	Mercury	nr		
	Molybdenum	17		
	Neodymium	nr		
	Nickel	180		
	Potassium (%)	nr		
	Rubidium	151		
	Samarium	4.1		
	Scandium	10.7		
	Selenium	<10		
	Silver	<5		
	Sodium (%)	2.27		
	Strontium	nr		
	Tantalum	<2		
	Tellurium	<20		
	Terbium	<1		
	Thorium	21.9		
	Tin	<200		
	Tungsten	<2		
	Uranium	10		
	Ytterbium	1.9		
	Zinc	340		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163

Phone: +61 8 9314 2566 | Email: info@geostats.com.au

Website: www.geostats.com.au

GBM924-7

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: