

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

GBM924-8



Certified Control Values

Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	22854	1088	55	+/- 296.8
Copper (ppm)	15155	460	52	+/- 129.3
Zinc (ppm)	87	7	52	+/- 1.9
Lead (ppm)	46	6	49	+/- 1.7
Arsenic (ppm)	27	5	49	+/- 1.4
Cobalt (ppm)	1215	79	65	+/- 19.8
Silver (ppm)	3.4	0.4	48	+/- 0.11

Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	22236	1395	40	+/- 451.8
Copper (ppm)	14860	753	72	+/- 178.1
Zinc (ppm)	76	9	52	+/- 2.4
Lead (ppm)	44	8	56	+/- 2
Arsenic (ppm)	25	3	48	+/- 0.8
Cobalt (ppm)	1189	68	51	+/- 19.4
Silver (ppm)	3.2	0.5	64	+/- 0.11

CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	Control statistics were produced from results accumulated in the October-2024 round robin. The number of results used to certify each analyte is shown in the table above.	Antimony	0.4	Fe
<u>Material Description</u> This material is described as a Nickel ore ex Pilbara.	Arsenic	27	SiO ₂	16.2
	<u>Colour Designation (ISCC-NBS, SP440)</u> This material is olive gray in colour.	Barium	<100	Al ₂ O ₃
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.		Bromine	<2	TiO ₂
	<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	<10	MnO
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.		Caesium	<2	CaO
	<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Calcium (%)	nr	P
<u>Material Safety</u> This product is not hazardous and non-toxic.		Cerium	8	S
	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	Chromium	219	MgO
'nr': Not Reported		Cobalt	1290	K ₂ O
	Europium	<0.5	Na ₂ O	0.59
Gold (ppb)	868	LOH1000	14.26	
Hafnium	<5			
Iridium (ppb)	154			
Iron (%)	37			
Lanthanum	6			
Lutetium	<0.2			
Mercury	nr			
Molybdenum	<10			
Neodymium	nr			
Nickel	24500			
Potassium (%)	nr			
Rubidium	<25			
Samarium	1.1			
Scandium	9.4			
Selenium	10			
Silver	<5			
Sodium (%)	0.36			
Strontium	nr			
Tantalum	<2			
Tellurium	<20			
Terbium	<1			
Thorium	0.6			
Tin	<200			
Tungsten	5			
Uranium	<1			
Ytterbium	<0.5			
Zinc	<200			
Zirconium	<500			

20 Hines Road, O'Connor, Western Australia 6163

Phone: +61 8 9314 2566 | Email: info@geostats.com.au

Website: www.geostats.com.au

GBM924-8

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: