

# GEOSTATS PTY LTD

Mining Industry Consultants  
Reference Material Manufacture and Sales

## Certified Low Level Gold Reference Material Product Code

# GLG924-5

### Certified Control Values

#### Low Level Gold

Gold Grade 20.99 ppb  
Standard Deviation 5.56 ppb  
Confidence Interval +/- 1.24 ppb



### CRM Details

<u>Control Statistic Details</u> Control statistics were produced from results accumulated in the October-2024 round robin. A total of 81 gold assays were used to certify this material.	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	<u>Material Description</u> This material is described as a Low grade sulphide - Pilbara, Western Australia.	Antimony	11.7	Fe
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is very light gray in colour.	Arsenic	84	SiO <sub>2</sub>	63.61
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Barium	267	Al <sub>2</sub> O <sub>3</sub>	14.15
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Bromine	<2	TiO <sub>2</sub>	0.74
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cadmium	<10	MnO	0.08
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Caesium	7	CaO	3.45
<u>Material Safety</u> This product is not hazardous and non-toxic.	Calcium (%)	nr	P	0.069
	Cerium	44	S	0.11
	Chromium	31	MgO	2.3
	Cobalt	13	K <sub>2</sub> O	2.17
	Europium	0.9	Na <sub>2</sub> O	1.72
	Gold (ppb)	19	LOI1000	6.06
	Hafnium	<5		
	Iridium (ppb)	<50		
	Iron (%)	3.8		
	Lanthanum	22		
	Lutetium	0.3		
	Mercury	nr		
	Molybdenum	<10		
	Neodymium	nr		
	Nickel	<100		
	Potassium (%)	nr		
	Rubidium	82		
	Samarium	3.7		
	Scandium	11.5		
	Selenium	<10		
	Silver	<5		
	Sodium (%)	1.23		
	Strontium	nr		
	Tantalum	<2		
	Tellurium	<20		
	Terbium	1		
	Thorium	7.2		
	Tin	<200		
	Tungsten	4		
	Uranium	2		
	Ytterbium	1.8		
	Zinc	<200		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163  
Phone: +61 8 9314 2566 | Email: info@geostats.com.au  
Website: www.geostats.com.au

GLG924-5

Geostats Pty Ltd, Certified Low Level Gold Reference Material, Product Code: